

CP-1221

Chekad CP-1221 is a hydroxylated solid polyester resin designed to cured with isocyanate for polyurethane powder coatings.

Final film properties

87/13 ratio, Suitable for texture coating.

Resin properties

Property	Unit	Value	Test method
Appearance	-	pale flakes	-
Hydroxyl Value	mgKOH/g	26-36	ASTM D 1639
Viscosity	CP@200°C	5000-10000	ASTM D 4287
Glass transition temp (Tg)	°C	≥69	ASTM E 1356
Color	Gardner	< 2	ASTM D 1544

Packaging

25 Kg bags or big bags.

Storage

Store in a cool and dry place.

Keep away from heat sources and direct sunlight.

Starting formulation

RM	Manufacturer	Formula
Hydroxyl Resin (CP-1221)	Chekad	522
ICN Hardner(Veatagon B 1530)	SSC	78
Flow agent (GIP 288)	SSC	10
Benzoin	SSC	4
Blanc fixe (HY-PBS)	Hoyonn	86
Tio2	Lomon	300

Extrusion condition	Film properties	Cure cycle
Twin-screw extruder (preferably)	Impact: 50 (kg*cm)	10 minutes / 200°C
Barrel Temperature: 110-115 (°C)	Gloss (60°): > 90	
Speed: 300 (rpm)	Adhesion: Excellent	

Note: Given information in this TDS is just for consumer guidance, please make sure of the resin suitability before use.



Shimi Pooshesh Kala Co.(Chekad)

Office: Unit# 52, Golbarg Commercial Center, Janbazan Ave., Narmak, Tehran-Iran

Tel: 0098-21-72531000 Fax: 0098 –21-77955874 www.chekad.com