

## **CP-7112**

Chekad CP-7112 is a carboxylated polyester resin designed for 70/30 formulation of hybrid powder coatings.

#### **Final film properties**

High glass, High wetting, Suitable for texture coatings.

### **Resin properties**

Property	Unit	Value	Test method
Appearance	-	pale flakes	-
Acid value	mgKOH/g	28-34	ASTM D 1639
Viscosity	CP@200°C	1000-3500	ASTM D 4287
Glass transition temp (Tg)	°C	≥54	ASTM E 1356
Color	Gardner	< 2	ASTM D 1544

### **Packaging**

25 Kg bags or big bags.

#### **Storage**

Store in a cool and dry place.

Keep away from heat sources and direct sunlight.

# **Starting formulation**

RM	Manufacturer	Formula
Polyester Resin (CP-7112)	Chekad	420
Epoxy Resin (CE 12 ; EEW 720)	Chekad	180
Flow agent (GIP 288)	SSC	10
Benzoin	SSC	4
Blanc fixe (HY-PBS)	Hoyonn	86
Tio2	Lomon	300

Extrusion condition	Film properties	Cure cycle
Twin-screw extruder (preferably)	Impact: 50 (kg*cm)	10 minutes / 200 °C
Barrel Temperature: 95-100 (°C)	Gloss (60°): > 90	
Speed: 300 (rpm)	Adhesion: Excellent	

Note: Given information in this TDS is just for consumer guidance, please make sure of the resin suitability before use.



Shimi Pooshesh Kala Co.(Chekad)

Office: Unit# 52, Golbarg Commercial Center, Janbazan Ave., Narmak, Tehran-Iran

Tel: 0098-21-72531000 Fax: 0098 -21-77955874