UPSIL® 200 HYDROPHILIC FUMED SILICA



Description

UPSIL® 200 is a kind of hydrophilic fumed silica with a specific surface area of 200 m /g. It's high purity white colloidal powder.

Applications

- HTV and RTV silicone rubber
- Adhesives and sealants
- · Paints, coatings and pigments
- Printing inks
- Cable compounds
- Unsaturated polyester resins, laminated resins and Gel coats

Packaging and Storage

 UPSIL® 200 is supplied in 10kg kraft paper bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances.

Advantages

- Rheology and thixotropy control of liquid systems, binders, polymers, etc.
- Used as anti-settling, thickening, anti-sagging agent
- Improvement of free flow and anti-caking characteristics of powders
- High transparency
- · Reinforcement filler in elastomers

Properties

Fioheines			
Properties and test methods	Unit	Typical Value	Standardization
Specific surface area (BET)	m²/g	200 ± 25	GB/T10722
pH value (in 4% dispersion)		3.6 ~ 4.5	GB/T1717
Loss on drying (2 hours at 105 °C)	Wt%	≤ 1.5	GB/T5211.3
Loss on ignition (2 hours at 1000 °C, based on material dried for 2 hours at 105 °C)	Wt%	≤ 2.5	GB/T20020
Sieve residue (45 µm)	%	≤ 0.05	GB/T5211.14
Silica content (based on ignited material)	Wt%	≥ 99.8	GB/T20020
Tamped density (based on material dried for 2 hours at 105 °C)	g/L	25 ~ 60	GB/T5211.4
Carbon content (based on material dried for 2 hours at 105 °C)	Wt%	≤ 0.2	GB/T20020

Oversea Partner

Shimi Pooshesh Kala Co.

Add: Unit 57, Golbarg Commercial Center, Janbazan Ave,

Narmak, Tehran, Iran Tel: +982172531000

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. UPSIL guarantees that its products comply with its sales specifications. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and UPSIL is at their disposal to supply any additional information.